

# 8327GL6



## Non-Silicone Liquid Thermal Gel

8327GL6 is a 1-part, silicone-free, paste-like gel offering extreme thermal conductivity and flame retardancy. This form-in-place, non-curable gel is easy to dispense and conforms to the component/heatsink interface, ensuring all air is displaced and eliminating hotspots. Its low modulus and robust temperature range allows for high heat dissipation, low component stress and thermal cycling stability. Circuits can be powered up immediately following application, offering exceptional convenience.

It is most often used as a gap filler on heatsinks to CPUs, LEDs, and other electronic components. Its high thermal conductivity makes it ideal for energy-intensive devices like telecommunications equipment, PCs for gamers and electric vehicle battery packs.



## Features & Benefits

- Extreme thermal conductivity
- Flame retardant—meets UL94 V-0
- 1-part, non-curable, dispensable gel
- Zero pump out—no slump under low pressure
- Silicone-free, will not contaminate surfaces
- Low modulus, ideal for aggressive thermal cycling conditions

## Available Packaging

Cat. No.	Packaging	Net Wt.
8327GL6-25ML	Jar	54 g
8327GL6-30ML	Cartridge	66 g
8327GL6-180ML	Cartridge	294 g

## Contact Information

MG Chemicals, 1210 Corporate Drive  
Burlington, Ontario, Canada L7L 5R6

Email: [support@mgchemicals.com](mailto:support@mgchemicals.com)

Phone: North America: +(1)800-340-0772

International: +(1) 905-331-1396

Europe: +(44)1663 362888

## Properties

Color	Grey
Resistivity	$10^9 \Omega \cdot \text{cm}$
Dissipation Factor @ 1 kHz	0.005
Breakdown Voltage @ 1 mm	3 200 V
Thermal Conductivity @ 25 °C	6.0 W/(m·K)
Flow Rate @ 90 psi, 0.1" orifice	4–6 g/min
Service Temperature Range	-40–120 °C
Intermittent Temperature	150 °C
Bond Line Thickness	<25 $\mu\text{m}$
Density	2.3 g/mL
Viscosity @ 25 °C	7 000 Pa·s

## Storage and Handling

Store between 16 and 27 °C in a dry area, away from sunlight (see SDS).

## Disclaimer

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.