



CarbonX™ Carbon Fiber High Temp Nylon (HTN) 3D Filament

Physical Properties	Standard	Unit	Typical Value
Density	ISO 1183	g/cc	1.24

Mechanical Properties	Standard	Unit	Typical Value
Tensile Strength, Break	ISO 527	MPa	87
Tensile Modulus	ISO 527	MPa	8200
Tensile Elongation, Break	ISO 527	%	1.9
Flexural Strength	ISO 178	MPa	95
Flexural Modulus	ISO 178	MPa	7895

Thermal Properties	Standard	Unit	Typical Value
Glass Transition Temperature (T _g)	DSC	°C	125
Deflection Temperature at 0.45 MPa (66psi)	ISO 75	°C	240
Melt Temperature (T _m)	DSC	°C	265

Electrical Property	Standard	Unit	Typical Value
Surface Resistance	ASTM D257	Ohm/sq	>10 ⁹

Printed Specimen Conditions
Printer: Open Source FDM/FFF
Nozzle: 0.4mm
Layer Height: 0.25mm
Infill: 100%, +/- 45°
Extrusion Temp: 295°C
Bed Temp: 130°C
Specimen Orientation: XY Flat