



CMC016010006H


110 Delta Drive
Pittsburgh, PA 15238
NAFTA Sales: (1) 800-245-3984
HK Sales: (852) 3102-9337
magnetics@spang.com
www.mag-inc.com

Dimensions				
	Bare (mm)	tol +/-	Case (mm)	tol +/-
OD (A)	16.0	typ	17.8	0.40
ID (B)	10.0	typ	8.2	0.40
HT (C)	6.0	typ	7.9	0.40

A_L ($\mu\text{H}/\text{T}^2$)	Conditions	
43.0 +/- 30%	10 kHz	2 mT
9.0 Min	100 kHz	2 mT

A_e (cm^2)	L_e (cm)	Weight (g)	Color
0.15	4.1	4.5 (Ref)	Black

PBT Class B (130°C)



Material	Nanocrystalline
Saturation Flux Density	1.25 Tesla
Permeability	93,000
Curie Temperature	560 °C
Continuous working Temperature	-40 °C to +130 °C