

Super Glue - Thick Viscosity - Big Gap Filling 1.0oz

Product Highlights

Rubber reinforced big gap filling super glue.

Use for joints that will not fit tight and when flexibility and vibration resistance are needed.

Bonds: Metal, Plastic, Wood, Cardboard, Paper, Ceramic, Leather and More!

Specifications

Viscosity:	700 cP (700 mPas)
Curing Time:	45 seconds
Main Ingredient:	Cyanoacrylate
Thermal Conductivity (after curing):	0.2 W/mK
Operating Temperature (after curing):	-30°C to 90°C (-22°F to 194°F)
Size:	30ml Squeeze Bottle



Storage and Handling

Store at 3-25°C (37-77°F). Do not freeze. Allow 4 hours for thermoset chip glue to reach an operating temperature of 20-25°C (68-77°F) before use.

Shelf Life

>24 months (unopened)

Transportation

This product has no shipping restrictions, when total shipment volume of Super Glue does not exceed 1000ml (qty 33 of 30ml bottles). Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.

Chip Quik Super Glue Available Part Numbers

Orderable Part Number	Viscosity	Curing Time	Main Ingredient	Thermal Conductivity	Operating Temperature	Size
SG1-0.5	5cP	3 seconds	Cyanocrylate	0.2 W/mK	-30°C to 90°C (-22°F to 194°F)	15 ml
SG1-1.0	5cP	3 seconds	Cyanocrylate	0.2 W/mK	-30°C to 90°C (-22°F to 194°F)	30 ml
SG2-0.5	100 cP	15 seconds	Cyanocrylate	0.2W/mK	-30°C to 90°C (-22°F to 194°F)	15 ml
SG2-1.0	100 cP	15 seconds	Cyanocrylate	0.2W/mK	-30°C to 90°C (-22°F to 194°F)	30 ml
SG3-0.5	700 cP	45 seconds	Cyanocrylate	0.2 W/mK	-30°C to 90°C (-22°F to 194°F)	15 ml
SG3-1.0	700 cP	45 seconds	Cyanocrylate	0.2 W/mK	-30°C to 90°C (-22°F to 194°F)	30 ml
SG4-1.0	700 cP	45 seconds	Cyanocrylate	0.2W/mK	-30°C to 90°C (-22°F to 194°F)	30 ml