

LINEAR TECHNOLOGY MATERIALS DECLARATION

1t1999mpms8-20f#pbf

(Engineering Calculation)

MSOP

(printed on: 2020-07-11 20:22:41)

TOTAL MASS (g) : 0.027152

| COMPONENT MATERIAL | VENDOR/ INDUSTRY NAMES | CONSTITUENT NAME | CAS NUMBER | CONSTITUENT MASS (g) | CONSTITUENT (PPM) OF MATERIAL | CONSTITUENT (PPM) OF TOTAL PKG. | | |
|--------------------------------|----------------------------------|--------------------------------|------------|----------------------|-------------------------------|---------------------------------|----------------|----------------------|
| Active Device | Linear Technology | Silicon (Si) | 7440-21-3 | 0.001914 | 1000000 | 70491.9765625 | | |
| Die Coat | Dow Corning | Silicone | 69430-27-9 | 0.000000 | 0 | 0 | | |
| Lead Frame | A42 | Copper (Cu) | 7440-50-8 | 0.000000 | 0 | 0 | | |
| | | Iron (Fe) | 7439-89-6 | 0.006206 | 580000 | 228564.90625 | | |
| | | Phosphorus (P) | 7723-14-0 | 0.000000 | 0 | 0 | | |
| | | Zinc (Zn) | 7440-66-6 | 0.000000 | 0 | 0 | | |
| | | Nickel (Ni) | 7440-02-0 | 0.004494 | 420000 | 165512.515625 | | |
| | | Silicon (Si) | 7440-21-3 | 0.000000 | 0 | 0 | | |
| | | Magnesium (Mg) | 7439-95-4 | 0.000000 | 0 | 0 | | |
| | | Tin (Sn) | 7440-31-5 | 0.000000 | 0 | 0 | | |
| Lead Frame Total: | | | | 0.010700 | 1000000 | 394077.40625 | | |
| Plating | PMI | Exter. Plating Pb | 7439-92-1 | 0.000000 | 0 | 0 | | |
| | | Exter. Plating Sn | 7440-31-5 | 0.000710 | 1000000 | 26149.9804688 | | |
| | | External Plating Total: | | | | 0.000710 | 1000000 | 26149.9804688 |
| | | Inter. Plating Ni | 7440-02-0 | 0.000000 | 0 | 0 | | |
| | | Inter. Plating Ag | 7440-22-4 | 0.000086 | 1000000 | 3167.35107422 | | |
| Internal Plating Total: | | | | 0.000086 | 1000000 | 3167.35107422 | | |
| Die Attach | ELECTRICALLY CONDUCTIVE ADHESIVE | Silver (Ag) | 7440-22-4 | 0.000669 | 750000 | 24639.0449219 | | |
| | | Tin (Sn) | 7440-31-5 | 0.000000 | 0 | 0 | | |
| | | Lead (Pb) | 7439-92-1 | 0.000000 | 0 | 0 | | |
| | | Silica (SiO2) | 60676-86-0 | 0.000000 | 0 | 0 | | |
| | | Indium (In) | 7440-74-6 | 0.000000 | 0 | 0 | | |
| | | Metal Oxide | | 0.000000 | 0 | 0 | | |
| | | Antimony (Sb) | 7440-36-0 | 0.000000 | 0 | 0 | | |
| | | Resin (EP) | | 0.000223 | 250000 | 8213.015625 | | |
| Die Attach Total: | | | | 0.000892 | 1000000 | 32852.0625 | | |
| Encapsulation | MULTI-AROMATIC RESIN Br/Sb FREE | Resin (EP) | | 0.001659 | 130000 | 61100.4140625 | | |
| | | Bromine (Br) | 40039-93-8 | 0.000000 | 0 | 0 | | |
| | | Silica (SiO2) | 60676-86-0 | 0.010591 | 830000 | 390063 | | |
| | | Antimony Trioxide (Sb2O3) | 1309-64-4 | 0.000000 | 0 | 0 | | |
| | | Metal Hydroxide | | 0.000447 | 35000 | 16462.8613281 | | |
| | | Carbon Black (C) | 1333-86-4 | 0.000064 | 5000 | 2357.09838867 | | |
| | | Encapsulation Total: | | | | 0.012761 | 1000000 | 469983.34375 |
| Bond Wire Estimated | AFW/TANAKA/ Kn | Gold (Au) | 7440-57-5 | 0.000089 | 1000000 | 3277.84008789 | | |
| | | | | | TOTAL MASS (g) : | 0.027152 | | |