



B-522 THERMAL TRANSFER PRINTABLE GLOSSY CLEAR POLYESTER LABEL STOCK

TDS No. B-522
 Effective Date: 08/12/2020

Description:

GENERAL

Print Technology: Thermal Transfer

Materials Type: Clear Polyester

Finish: Glossy

Adhesive: Removable acrylic

APPLICATIONS

Alphanumeric and barcode applications such as electronic component marking and general purpose applications that require good solvent resistance, heat resistance and clean removability.

RECOMMENDED RIBBONS

- Brady Series R6000 Halogen Free
- Brady Series R4900 (alternate)
- Brady Series R6200 (alternate)
- Brady Series R4400 (White and Red) (alternate)

REGULATORY

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

In Canada: www.bradycanada.ca/weee-rohs

In Europe: www.bradyeurope.com/rohs

In Japan: www.brady.co.jp/products/labelsuse/rohs

All other regions: www.bradyid.com/weee-rohs

Details:

PHYSICAL PROPERTIES	TEST METHOD	AVERAGE RESULTS
Thickness	ASTM D 1000 -Substrate -Adhesive -Total (excluding liner)	0.002 inch (0.0508 mm) 0.001 inch (0.0254 mm) 0.003 inch (0.0762 mm)
Adhesion to: -Stainless Steel	ASTM D 1000 20 minute dwell 24 hour dwell	23 oz/inch (25 N/100 mm) 27 oz/inch (30 N/100 mm)
-Aluminum	20 minutes dwell 24 hour dwell	19 oz/inch (21 N/100 mm) 34 oz/inch (37 N/100 mm)
-Polypropylene	20 minutes dwell 24 hour dwell	9 oz/inch (9.8 N/100 mm) 6 oz/inch (6.6 N/100mm)
-Glass	20 minutes dwell 24 hour dwell	29 oz/in (32 N/100 mm) 30 oz/in (33 N/100 mm)
Dielectric Strength	ASTM D 1000	8424 volts
SAFT, °C	TM-10048	205°C

*B- 522 removes cleanly from the surfaces listed above.

Performance properties tested on B-522 printed with the Brady Series R6000 Halogen Free Series ribbons. Printed samples were laminated to aluminum and allowed to dwell 24 hours before exposure to the indicated environments. Labels were tested for removability after exposure to environmental conditions.

PERFORMANCE PROPERTIES	TEST METHOD	TYPICAL RESULTS
Long Term High Service Temperature	30 days at various temperatures	No visible effect to 100°C. 110°C slight discoloration, 145°C moderate discoloration, 160°C label is no longer cleanly removable and discolored
Low Service Temperature	30 days at -70°C	No visible effect, cleanly removable
Short Term High Service Temperature	5 minutes at various temperatures	No visible effect and cleanly removable at 180°C. At 210°C label is slightly discolored but remains removable from the test panel with slight adhesive residue. At 230°C label has shrunk to the extent that it is non- functional.
Humidity Resistance	30 days at 100°F (37°C) and 95% relative humidity.	Removable with minor adhesive residue, slight label discoloration
UV Light Resistance	ASTM G155 Cycle 1 (no spray) 30 days in Xenon test chamber	Not suited for outdoor use, non-removable
Weatherability	ASTM G155, Cycle 1 30 days in Xenon Arc Weather-Ometer®	Not suited for outdoor use, non-removable
Salt Fog Resistance	ASTM B 117 30 days in 5% salt fog solution chamber	No visible effect on label, cleanly removable
Abrasion Resistance	Taber Abraser, CS10 grinding wheels, 250 g/arm (Fed. Std. 191A, Method 5306)	Print legible after 150 cycles

PERFORMANCE PROPERTY	CHEMICAL RESISTANCE
----------------------	---------------------

Samples were printed with the Brady Series R6000 Halogen Free ribbon. Samples were laminated to aluminum panels and allowed to dwell 24 hours prior to testing. Testing was conducted at room temperature and consisted of 30 minute immersions in the specified test fluid. After immersion, the samples were removed from the test fluid and the printed image rubbed 10 times with a cotton swab saturated with the test fluid. The rating scale below shows the effect to the quality of the print for each sample. Samples were also tested for removability*.

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE		
	EFFECT TO LABEL STOCK	EFFECTS TO PRINTED IMAGE	
		R6000 Halogen Free	
		WITHOUT RUB	WITH RUB
10% Sodium Hydroxide Solution	No visible effect	1	1
10% Sulfuric Acid solution	No visible effect	1	1
BIO- ACT® EC -7R™	Slight edge lift	1	1
Acetone	No visible effect	1	5
Methyl Ethyl Ketone (MEK)	No visible effect	1	5
3% Alconox® Detergent Solution	No visible effect	1	1

Windex®	No visible effect	1	1
Toluene	No visible effect	1	5
Isopropyl Alcohol	No visible effect	1	1
Mineral Spirits	No visible effect	1	1
Gasoline	No visible effect	1	2
JP-8 Jet Fuel	No visible effect	1	1
Brake Fluid DOT 3	No visible effect	1	4
Skydrol® 500B-4	No visible effect	1	5
SAE 20 WT Oil at 70°C	No visible effect	1	1
MIL 5606A Oil	No visible effect	1	1
Formula 409® Cleaner	No visible effect	1	1
Northwoods™ Buzz Saw Citrus Degreaser	No visible effect	1	1
Deionized Water	No visible effect	1	1

Rating Scale:

1= no visible effect

2= slight smear or print removal, detectable but minimal smear

3= moderate smear or print removal (print still legible)

4= severe smear or print removal (print illegible or just barely legible)

5= complete print and/or topcoat removal

NP= print removed prior to rub

* B- 522 removed cleanly from aluminum after tested in the solvents listed above.

Shelf Life:

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

Trademarks:

ASTM: American Society for Testing and Materials (U.S.A.)

Alconox® is a registered trademark of Alconox Co.

BIOACT® is a registered trademark of Petroferm, Inc.

EC -7R™ is a trademark of Petroferm Inc.

Formula 409® is a registered trademark of the Clorox Company

Northwoods™ is a trademark of the Superior Chemical Corporation.

SAE: Society of Automotive Engineers (U.S.A.)

Skydrol® is a registered trademark of Solutia Inc.

Weather-Ometer® is a registered trademark of Atlas Material Testing Technology LLC

Windex® are registered trademarks used under authority of S.C. Johnson & Son, Inc.

All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information. Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and

assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2020 Brady Worldwide, Inc. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.

Brady North America | 6555 W. Good Hope Rd | Milwaukee, WI 53223 | USA | Tel: 414-358-6600 | Fax: 800-292-2289