



BERGQUIST BOND PLY TBP 850

Known as BERGQUIST BOND-PLY 100
August 2021

PRODUCT DESCRIPTION

Thermally Conductive, Fiberglass Reinforced Pressure Sensitive Adhesive Tape.

Technology	Acrylic
Appearance	White
Reinforcement Carrier	Fiberglass
Total Thickness , ASTM D374	0.127, 0.203, 0.279 mm
Application	Thermal management, Thermally conductive adhesive
Operating Temperature Range	-40 to 120°C

FEATURES AND BENEFITS

- Thermal impedance: 0.52°C.in² /W @ 50 psi
- High bond strength to a variety of surfaces
- Double-sided, pressure sensitive adhesive tape
- High performance, thermally conductive acrylic adhesive
- Can be used as an alternate of heat-cure adhesive, screw mounting or clip mounting

TYPICAL APPLICATIONS

- Mount heat sink onto BGA graphic processor or drive processor
- Mount heat spreader onto power converter PCB or onto motor control PCB

SHELF LIFE

The double-sided, pressure sensitive adhesive used in LOCTITE BERGQUIST BOND PLY® products requires the use of dual liners to protect the surfaces from contaminants.

The recommended shelf life for BERGQUIST BOND PLY TBP 850 is 6 months at a maximum continuous storage temperature of 35°C or 3-months at a maximum continuous storage temperature of 45°C, for maintenance of controlled adhesion to the liner.

The shelf life of the Bond Ply material, without consideration of liner adhesion (which is often not critical for manual assembly processing), is recommended at 12 months from date of manufacture at a maximum continuous storage temperature of 60°C.

TYPICAL PROPERTIES

Physical Properties

Temperature Coefficient of Resistance, °C	200
Elongation , 45° to warp and fill, ASTM D412,%	70
Coefficient of Thermal Expansion, ASTM D 3386	325 , ppm
Glass Transition Temperature, ASTM D1356, °C	-30
Flammability Rating, UL 94	V-0
Tensile Strength, ASTM D412	MPa 6 (psi) (900)

Adhesion Properties

Lap Shear Strength, ASTM D1002:	
@ 25°C	MPa 0.7 (psi) (100)
After 5 hours @ 100°C	MPa 1.4 (psi) (200)
After 2 minutes @ 200°C	MPa 1.4 (psi) (200)
Static Dead Weight Shear Strength, PSTC#7, °C	150

Electrical Properties

Dielectric Breakdown Voltage, ASTM D149:	
@ 0.005" (Vac)	3,000
@ 0.008" (Vac)	6,000
@ 0.011" (Vac)	8,500

Thermal Properties

Thermal Conductivity , ASTM D5470, W/(m-K)	0.8
--	-----

Thermal Impedance vs. Pressure

TO-220 Thermal Performance, °C/W:	
@ 0.005":	
@ 10 psi	5.17
@ 25 psi	4.87
@ 50 psi	4.49
@ 100 psi	4.18
@ 200 psi	4.1



@ 0.008":	
@ 10 psi	5.4
@ 25 psi	5.35
@ 50 psi	5.28
@ 100 psi	5.22
@ 200 psi	5.2

@ 0.011":	
@ 10 psi	6.59
@ 25 psi	6.51
@ 50 psi	6.51
@ 100 psi	6.5
@ 200 psi	6.4

Thermal Impedance, ASTM D5470, °C-in²/W⁽¹⁾:

@ 0.005":	
@ 10 psi	0.56
@ 25 psi	0.54
@ 50 psi	0.52
@ 100 psi	0.5
@ 200 psi	0.5

@ 0.008":	
@ 10 psi	0.82
@ 25 psi	0.8
@ 50 psi	0.78
@ 100 psi	0.77
@ 200 psi	0.75

@ 0.011":	
@ 10 psi	1.03
@ 25 psi	1.02
@ 50 psi	1.01
@ 100 psi	1.0
@ 200 psi	0.99

¹⁾ The ASTM D5470 test fixture was used. The recorded value includes interfacial thermal resistance. These values are provided for reference only. Actual application performance is directly related to the surface roughness, flatness and pressure applied.

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

CONFIGURATIONS AVAILABLE

BERGQUIST BOND PLY TBP 850 are supplied in:

- Sheet form
- Roll form
- Die-Cut parts

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb/F}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 3