

Description

The 600 Series *Positive Presensitized Copper Clad Boards* are made of a translucent laminate consisting of a continuous woven glass cloth impregnated with epoxy resin. The boards are made of FR4, which is a flame retardant version of G-10 material.

The boards are ideal for prototyping and small production runs. It is used by the circuit processing industries and students.

Benefits and Features

- **1 oz copper boards (1.37 mil, 35 µm)**
- **Flammability meets UL 94V-0 (file # E98983)**
- **High heat resistance**
- **UV blocking**
- **Comes in single-sided and double-sided boards of 1/16" (1.60 mm) and 1/32" (0.80 mm) thicknesses**

Properties

<i>Physical Properties</i>	<i>Method</i>	<i>Specification</i>	<i>Typical Value</i>
Moisture Absorption Flammability	IPC-TM-650 2.6.2.1 UL-94	<0.35% Meets	0.05-0.3% 94V-0
<i>Mechanical Properties</i>	<i>Method</i>	<i>Specification</i>	<i>Typical Value</i>
Peel Strength, 1 oz	IPC-TM-650 2.4.8	>6 lb/in	10-14 lb/in
<i>Thermal Properties</i>	<i>Method</i>	<i>Specification</i>	<i>Typical Value</i>
Glass Transition Temperature (T _g)	IPC-TM-650 2.4.25	—	130-145 °C
CTE prior T _g , Z-axis	IPC-TM-650 2.4.24	—	50-70 ppm/°C
CTE after T _g , Z-axis	"	—	250-350 ppm/°C
Dimensional Stability, X-Y axis	IPC-TM-650 2.4.39	<0.05%	0.005-0.03%
Thermal Stress	IPC-TM-650 2.4.13.1	>10 s	>200 s
Decomposition Temperature @5% weight loss	IPC-TM-650 2.4.24.6	—	310 °C



ISO 9001 Registered Quality System.
Burlington, Ontario, Canada QMI File # 004008

Positive Presensitized Copper Clad Boards 600 Series Technical Data Sheet

600-Series

<i>Electrical Properties</i>	<i>Method</i>	<i>Specification</i>	<i>Typical Value</i>
Dielectric Breakdown	IPC-TM-650 2.5.6	>40 kV	>60 kV
Volume Resistivity	IPC-TM-650 2.5.17	>10 ⁶	5 x 10 ⁸ to 5 x 10 ⁹ mΩ·cm
Surface Resistivity	"	>10 ⁴	5 x 10 ⁶ to 5 x 10 ⁷ mΩ·cm
Arc Resistance	IPC-TM-650 2.5.1	>60 s	>120 s
Dielectric Constant @1 MHz	IPC-TM-650 2.5.5.9	<5.4	4.2-4.7
@1 GHz	"	—	3.8-4.2
Dissipation Factor @1 MHz	"	<0.035	0.015-0.020
@1 GHz	"	—	0.012-0.014

Note: Typical values for reference only. Values tested with 0.020-0.062" sample.

Storage and Shelf Life

Store at around room temperature 18 to 27 °C [65 to 80 °F] and protect from direct heat or sunlight. Keep sealed in an air tight container, away from humidity.

Health and Safety

Please see the *600 Series Positive Presensitized Copper Clad Boards Safety Data Sheet* (SDS) for more details on transportation, storage, handling and other security guidelines.

Packaging and Supporting Products

Available Sizes

FR4 1/16" (1.60 mm), double sided

<i>Cat. No.</i>	<i>Metric</i>	<i>Imperial</i> ^{a)}
660	152 x 230 mm	6" x 9"

FR4 1/32" (0.80 mm), single sided

<i>Cat. No.</i>	<i>Metric</i>	<i>Imperial</i> ^{a)}
689	150 x 230 mm	6" x 9"

FR4 1/32" (0.80 mm), double sided

<i>Cat. No.</i>	<i>Metric</i>	<i>Imperial</i> ^{a)}
690	150 x 230 mm	6" x 9"

a) Sizes are approximate

Supporting Products

- *Positive Presensitized Copper Clad Boards 600 Series*
- *Copper Clad boards (Half Ounce) 500 Series (Half Ounce)*



ISO 9001 Registered Quality System.
Burlington, Ontario, Canada QMI File # 004008

Positive Presensitized Copper Clad Boards 600 Series Technical Data Sheet

600-Series

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)
+(1) 905-331-1396 (International)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address: **Manufacturing & Support**
1210 Corporate Drive
Burlington, Ontario, Canada
L7L 5R6

Head Office
9347-193rd Street
Surrey, British Columbia, Canada
V4N 4E7

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.