PCN Nu	<b>PCN Number:</b> 20191104000.1A			1			F	CN Date:	Mar 23, 2020	
Title:Qualification of Hefei Tongfu Microelectronic Co. Ltd (HFTF) as additional Assembly Site for Select Devices										
Custom	Customer Contact:         PCN Manager         Dept:         Quality Services									
Change	Change Type:									
Asse	mbly Site	9			Desig	n 🗌 Wa		Wafer Bump	Wafer Bump Site	
Asse	embly Pro	cess			Data S	Sheet		Wafer Bump Material		
Asse	embly Mat	erial	S		Part n	Part number change		Wafer Bump Process		
Mechanical Specification			Test S	Test Site		Wafer Fab Site				
Packing/Shipping/Labeling			Test F	Process		Wafer Fab N	1aterials			
	Wafer Fab Process									

# **PCN Details**

## **Description of Change:**

The purpose of this Rev A is to notify the package marking change for **Group 3** devices. We apologize for any inconvenience this may have caused.

Texas Instruments is pleased to announce the Qualification of Hefei Tongfu Microelectronic Co. Ltd (HFTF) as additional Assembly Site for Select Devices listed in the "Product Affected" Section. Current assembly sites and Material differences are as follows.

## **Material Differences:**

### **Group 1 Device:**

	Hana Semiconductor	HFTF
Mount Compound	EY1000063	A-18
Mold compound	EN2000507	R-31
Wire type	Au	Cu

#### **Group 2 Device:**

	Hitachi Semiconductor	HFTF
Mount Compound	RZ241C	A-18
Mold compound	RM500F	R-31
Wire type	Au	Cu

# Group 3 Device:

	TIEM	HFTF
Mount Compound	4213245	A-03
Mold compound	8095181	R-27
Wire type	Au	Cu

Note: Wire type change for devices highlighted in green only.

# Package Marking Difference:

	TIEM	HFTF
Top Side	(CUST1) O O = PIN 1 INDICATOR (CUST 1) = CUSTOMER CODE	* * * * *     (CUST1)     * * * *      * * * = BINARY DATE CODE     (CUST 1) = CUSTOMER CODE     ■ = PIN 1 STRIPE

	Bottom Side	OYML YM = YEAR MONTH DATE CODE L = LAST DIGIT IN ASSEMBLY LOT CODE O = ORIENTATION DOT			
Reason fo	or Change:				
Continuity	of supply.				
Anticipat	ed impact on Fo	orm, Fit, Function, Quality or Reliability (positive / negative)	:		
None					
Anticipat		Aterial Declaration			
<ul> <li>No Impact to the Material Declaration</li> <li>Material Declaration</li> <li>Material Declaration</li> <li>Material Declaration</li> <li>Material Declaration</li> <li>Material Declaration</li> <li>Material Declaration</li> <li>Production data and will be available following the production release. Upon production release the revised reports can be obtained from the <u>TI Eco-Info website</u>. There is no impact to th material meeting current regulatory compliance requirements w this PCN change.</li> </ul>					
<b>Changes</b>	to product iden	ntification resulting from this PCN:			
Assembly	/ Site				
	niconductor	Assembly Site Origin (22L) ASO: HNT			
	emiconductor	Assembly Site Origin (22L) ASO: HTC			
TIEM HFTF		Assembly Site Origin (22L)ASO: CU6Assembly Site Origin (22L)ASO: HFT			
Sample product shipping label (not actual product label) TEXAS INSTRUMENTS MADE IN: Malaysia 20C: 20(: MSL 2 /260C/1 YEAR SEAL DT MSL 1 /235C/UNLIM 03/29/04 OPT: ITEM: 39 LBL: 5A (L)T0:1750 ABEL 101 CONSTRUCTION (222) (10) CONSTRUCTION (220) (10) 0336 (317)L0T: 3959047MLA (4W) TKY (1T) 7523483S12 (P) (2P) REV: (V) 0033317 (291) CS0: SHE (21L) CC0:USA (221) AS0: MLA (23L) ACO: MYS					
Product A	Affected Group	1:			

PCA9306DCUR	SN74LVC1G74DCUT	SN74LVC2G240DCUR	SN74LVC3G04DCUT			
PCA9306DCURG3	SN74LVC1G99DCUR	SN74LVC2G241DCUR	SN74LVC3G06DCUR			
PCA9306DCUT	SN74LVC1G99DCUT	SN74LVC2G241DCUT	SN74LVC3G06DCUT			
PCA9306DCUTG3	SN74LVC2G00DCUR	SN74LVC2G32DCUR	SN74LVC3G07DCUR			
PPCA9306DCUR	SN74LVC2G00DCUT	SN74LVC2G32DCUT	SN74LVC3G07DCUT			
SN74GTL2002DCUR	SN74LVC2G02DCUR	SN74LVC2G38DCUR	SN74LVC3G14DCUT			
SN74LVC1404DCUR	SN74LVC2G02DCUT	SN74LVC2G38DCUT	SN74LVC3G34DCUT			
SN74LVC1G123DCUT	SN74LVC2G08DCUT	SN74LVC2G74DCUT	SN74LVC3GU04DCUR			
SN74LVC1G139DCUR	SN74LVC2G126DCUR	SN74LVC2G79DCUR	SN74TVC3306DCUR			
SN74LVC1G139DCUT	SN74LVC2G126DCUT	SN74LVC2G80DCUR				
SN74LVC1G29DCUR	SN74LVC2G132DCUT	SN74LVC2G86DCUR				
SN74LVC1G29DCUT	SN74LVC2G157DCUR	SN74LVC2G86DCUT				
SN74LVC1G74DCUR	SN74LVC2G157DCUT	SN74LVC3G04DCUR				
Product Affected Group 2:						
LSF0102DCUR	SN74LVC2G74DCUR	SN74LVC3G14DCUR	SN74LVC3G34DCUR	7		
SN74LVC2G08DCUR	SN74LVC2T45DCUR	SN74LVC3G17DCUR				
Product Affected Grou	<mark>p 3:</mark>					

LM20BIM7/NOPB	LM20BIM7X/NOPB	LM20CIM7X/NOPB	LPV521MGE/NOPB
LM20BIM7X/E7001066	LM20CIM7/NOPB	LPV521MG/NOPB	LPV521MGX/NOPB

# **Qualification Report** Approve Date 30-Oct-2019

# **Qualification Results**

Data Displayed as: Number of lots / Total sample size / Total failed

Туре	Test Name / Condition	Duration	Qual Device: LSF0102DCUR	Qual Device: <u>SN74LVC1G123DCUR</u>
PC	PreCon Level 1	Level 1-260C	3/231/0	3/231/0
HAST	Biased HAST, 130C/85%RH	96 Hours	3/231/0	3/231/0
AC	Autoclave 121C	96 Hours	3/231/0	3/231/0
TC	Temperature Cycle, -65/150C	500 Cycles	3/231/0	3/231/0
HTSL	High Temp Storage Bake 170C	420 Hours	3/231/0	3/231/0
HTOL	Life Test, 125C	1000 Hours	3/231/0	3/231/0
LI	Lead Fatigue	Leads	3/66/0	-
LI	Lead Pull	Leads	3/18/0	-
MISC	Salt Atmosphere	24 Hours	3/66/0	-
SD	Surface Mount Solderability	PB	3/66/0	-
SD	Surface Mount Solderability	PB-Free	3/66/0	-
DS	Die Shear		3/30/0	3/30/0
PKG	Lead Finish Adhesion	Leads	3/45/0	-
WBP	Bond Pull	Wires	3/228/0	3/228/0
WBS	Bond Shear	Wires	3/228/0	3/228/0
FLAM	Flammability (IEC 695-2-2)		3/15/0	-
FLAM	Flammability (UL 94V-0)		3/15/0	-
FLAM	Flammability (UL-1694)		3/15/0	-

QBS: Qual By Similarity

- Qual Device SN74LVC1G123DCUR is qualified at LEVEL1-260CG

- Qual Device LSF0102DCUR is qualified at LEVEL1-260CG

- Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

- The following are equivalent HTOL options based on an activation energy of 0.7eV : 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

- The following are equivalent HTSL options based on an activation energy of 0.7eV : 150C/1k Hours, and 170C/420 Hours

- The following are equivalent Temp Cycle options per JESD47 : -55C/125C/700 Cycles and -65C/150C/500 Cycles

Quality and Environmental data is available at TI's external Web site: http://www.ti.com/

Green/Pb-free Status:

Qualified Pb-Free(SMT) and Green

# **Qualification Report**

Approve Date 12-Sept-2019

# **Qualification Results**

Data Displayed as: Number of lots / Total sample size / Total failed

Туре	Test Name / Condition	Duration	QBS Device: SN74AHC1G1 26DCKR	QBS Device: SN74CBT1G3 84DCKR	QBS Device: SN74LVC1G17 DCKR	QBS Device: SN74LVC2G04 DCKR
AC	Autoclave 121C	96 Hours	1/77/0	1/77/0	3/231/0	3/231/0
BHAST	Biased HAST, 130C/85%RH	96 Hours	-	-	3/231/0	3/231/0
ED	Electrical Characterization	Per Datasheet Parameters	1/30/0	1/30/0	3/90/0	3/90/0
ELFR	Early Life Failure Rate, 125C	48 Hours	-	-	-	-
HTOL	Life Test, 150C	300 Hours	-	-	3/231/0	3/231/0
HTOL	Life Test, 125C	1000 Hours	-	-	-	-
HTSL	High Temp. Storage Bake 170C	420 Hours	1/77/0	1/77/0	3/231/0	3/231/0
TC	Temperature Cycle, - 65C/150C	500 Cycles	1/77/0	1/77/0	3/231/0	3/231/0
UHAST	Unbiased HAST, 130C/85%RH	96 Hours	-	-	-	-
FLAM	Flammability (UL 94V-0)	Method A/UL 94V-0	-	-	3/15/0	3/15/0
LI	Lead Fatigue	Leads	-	-	3/66/0	3/66/0
LI	Lead Pull to Destruction	Leads	-	-	3/27/0	3/27/0
MQ	Manufacturability (Assembly)	(per mfg. site specification)	1/PASS	1/PASS	3/PASS	3/PASS
PD	Physical Dimensions	Per Mechanical Drawing	-	-	-	-
SD	Solderability	Steam Age, 8 Hours, Pb	-	-	3/66/0	3/66/0
SD	Solderability	Steam Age, 8 Hours, Pb Free	-	-	3/66/0	3/66/0
WBP	Bond Pull	76 Wires, 3 units min	1/76/0	1/76/0	3/228/0	3/228/0
WBS	Ball Bond Shear	76 Balls, 3 units min	1/76/0	1/76/0	3/228/0	3/228/0
XRAY	X-ray	(top side only)	-	-	-	-

Туре	Test Name / Condition	Duration	QBS Device: TLV9001IDCK R	QBS Device: OPA1671IDCK	QBS Device: LM66100DCK	Qual Device: TPS22948DCK
AC	Autoclave 121C	96 Hours	-	-	-	1/77/0

BHAST	Biased HAST, 130C/85%RH	96 Hours	6/262/0	3/231/0	-	1/77/0
ED	Electrical Characterization	Per Datasheet Parameters	1/30/0	3/90/0	1/30/0	1/30/0
ELFR	Early Life Failure Rate, 125C	48 Hours	-	3/2397/0	-	-
HTOL	Life Test, 150C	300 Hours	-	3/231/0	3/231/0	-
HTOL	Life Test, 125C	1000 Hours	-	-	-	3/231/0
HTSL	High Temp. Storage Bake 170C	420 Hours	3/231/0	3/231/0	-	1/77/0
тс	Temperature Cycle, - 65C/150C	500 Cycles	3/231/0	3/231/0	-	1/77/0
UHAST	Unbiased HAST, 130C/85%RH	96 Hours	3/231/0	3/231/0	-	-
FLAM	Flammability (UL 94V-0)	Method A/UL 94V-0	-	-	-	-
LI	Lead Fatigue	Leads	-	-	-	-
LI	Lead Pull to Destruction	Leads	-	-	-	-
MQ	Manufacturability (Assembly)	(per mfg. site specification)	3/PASS	3/PASS	1/PASS	1/PASS
PD	Physical Dimensions	Per Mechanical Drawing	-	3/15/0	-	-
SD	Solderability	Steam Age, 8 Hours, Pb	-	-	-	-
SD	Solderability	Steam Age, 8 Hours, Pb Free	-	-	-	-
WBP	Bond Pull	76 Wires, 3 units min	-	-	1/76/0	1/76/0
WBS	Ball Bond Shear	76 Balls, 3 units min	-	-	1/76/0	1/76/0
XRAY	X-ray	(top side only)	-	-	-	1/5/0

- QBS: Qual By Similarity

- Qual Device SN74AHC1G126DCKR is qualified at LEVEL1-260C

- Qual Device SN74CBT1G384DCKR is qualified at LEVEL1-260C

- Qual Device SN74LVC1G17DCKR is qualified at LEVEL1-260C

- Qual Device SN74LVC2G04DCKR is qualified at LEVEL1-260C

- Qual Device TLV9001IDCKR is qualified at LEVEL2-260C

- Qual Device OPA1671IDCK is qualified at LEVEL2-260C

- Qual Device LM66100DCK is qualified at LEVEL1-260C

- Qual Device TPS22948DCK is qualified at LEVEL1-260C

- Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, and HTSL, as applicable

- The following are equivalent HTOL options based on an activation energy of 0.7eV: 125C/1000 Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

- The following are equivalent HTSL options based on an activation energy of 0.7eV: 150C/1000 Hours, and 170C/420 Hours

- The following are equivalent Temperature Cycle options per JESD47: -55C/125C/700 Cycles and -65C/150C/500 Cycles

Quality and Environmental data is available at TI's external Web site: http://www.ti.com/

## Green/Pb-free Status:

Qualified Pb-Free (SMT) and Green

For questions regarding this notice, e-mails can be sent to the regional contacts shown below or your local Field Sales Representative.

Location	E-Mail
USA	PCNAmericasContact@list.ti.com
Europe	PCNEuropeContact@list.ti.com
Asia Pacific	PCNAsiaContact@list.ti.com
Japan	PCNJapanContact@list.ti.com

### IMPORTANT NOTICE AND DISCLAIMER

TI PROVIDES TECHNICAL AND RELIABILITY DATA (INCLUDING DATASHEETS), DESIGN RESOURCES (INCLUDING REFERENCE DESIGNS), APPLICATION OR OTHER DESIGN ADVICE, WEB TOOLS, SAFETY INFORMATION, AND OTHER RESOURCES "AS IS" AND WITH ALL FAULTS, AND DISCLAIMS ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR NON-INFRINGEMENT OF THIRD PARTY INTELLECTUAL PROPERTY RIGHTS.

These resources are intended for skilled developers designing with TI products. You are solely responsible for (1) selecting the appropriate TI products for your application, (2) designing, validating and testing your application, and (3) ensuring your application meets applicable standards, and any other safety, security, or other requirements. These resources are subject to change without notice. TI grants you permission to use these resources only for development of an application that uses the TI products described in the resource. Other reproduction and display of these resources is prohibited. No license is granted to any other TI intellectual property right or to any third party intellectual property right. TI disclaims responsibility for, and you will fully indemnify TI and its representatives against, any claims, damages, costs, losses, and liabilities arising out of your use of these resources.

TI's products are provided subject to TI's Terms of Sale (<u>www.ti.com/legal/termsofsale.html</u>) or other applicable terms available either on ti.com or provided in conjunction with such TI products. TI's provision of these resources does not expand or otherwise alter TI's applicable warranties or warranty disclaimers for TI products.